





---

<b>Description:</b>	Styrene maleic copolymer based product.
<b>Aspect:</b>	Colorless liquid.
<b>Concentration:</b>	11,0 – 15,0%
<b>pH (sol. 10%):</b>	8,0 – 10,0
<b>Charge:</b>	Anionic.
<b>Application:</b>	Before fatliquor, as a drum impregnation.
<b>Properties:</b>	<p><b>UNIESP® STM</b> water-soluble copolymer retanning agent for chrome-tanned leather. It is especially suitable for full grain and also for items that must subsequently be buffed, polished or embossed, both for footwear or clothing leathers.</p> <p><b>UNIESP® STM</b> imparts softness and tightness to the leather. It is highly recommended for the chrome leather retanning in the production of lightweight softy nappa leathers.</p>
<b>Use guideline:</b>	<p>We suggest diluting the <b>UNIESP® STM</b> in 3 parts of water, before to apply. The dose varies according the leather article:</p> <ul style="list-style-type: none"><li> Shoe Napa leather: 3 – 4% over shaved weight;</li><li> Upholstery leather: 4 – 5% over shaved weight;</li><li> Semi chrome leather: 2 – 4% over shaved weight;</li></ul>
<b>Storage:</b>	<p>We recommend keeping the product sealed in the original package, in a clean and controlled environment, avoiding extreme temperatures.</p> <div style="text-align: center;"></div>
<b>Package:</b>	30 Kg plastic drum, 190 Kg metal drum or 1.000 Kg IBC.