






### Inorganic salt with dispersion properties

---

<b>Description:</b>	Short chain sodium polyphosphate.
<b>Aspect:</b>	White powder.
<b>pH (sol. 10%):</b>	9,0 – 10,5
<b>Charge:</b>	Anionic.
<b>P<sub>2</sub>O<sub>5</sub> content:</b>	>56%
<b>Application:</b>	In the soaking, liming, vegetable tanning and dyeing leather process.
<b>Properties:</b>	<p><u>In the Soaking:</u></p> <p><b>UNIESP® NET II</b> is an alkaline agent that softens the water in the soaking process, which allows a better dispersion of the surfactants. This effect results in uniform wetting of the inner structure of the skins.</p> <p><u>In the Liming:</u></p> <p><b>UNIESP® NET II</b> enhances the dissolution of the lime, which results in its more uniform penetration. This gives a smooth swollen of the fibers, with less wrinkles and excellent opening.</p> <p><u>In the Vegetal Tanning:</u></p> <p>Small amounts of the <b>UNIESP® NET II</b> in the pickle, before the addition of the vegetable tannins, will provide a superficial reduction of the acidity. Thus, we reduced some of the tannin reactivity and accelerate the rate of penetration of tanning.</p> <p><u>In the chrome leather Dyeing:</u></p> <p>To reach a smooth alkaline effect, we recommend <b>UNIESP® NET II</b> to anionize the fibers before dye. This method provides a homogeneous distribution of the dyes inside the leather, revealing a more intense and uniform inner cut.</p>
<b>Use guideline:</b>	<p>We suggest to apply the <b>UNIESP® NET II</b> diluted in water, thru the drums funnel:</p> <ul style="list-style-type: none"><li> Soaking: 0,5 – 1,5% over the salted weight.</li><li> Liming: 0,2 – 0,7% over the salted weight.</li><li> Vegetal tanning: 1,0 – 3,0% over the limed weight.</li><li> Chrome tanned leather dye: 0,5 – 2,5% over shaved wet blue weight.</li></ul>
<b>Storage:</b>	<p>We recommend keeping the product sealed in the original package, in a clean and controlled environment, avoiding extreme temperatures.</p> 
<b>Package:</b>	25 Kg plastic bags in 1.000 Kg wood pallets.